

Technisches Datenblatt:
Technical Data Sheet:

EPDM 4300
EPDM 4300

EPDM EPDM	10.09.2019
Härte / Hardness (Shore A) DIN ISO 7619-1	60° –70°
Farbe / Colour	schwarz / <i>black</i>
Temperaturbereich / Temperature Range	-35°C / +100°C
Dichte / Density	1,47 g/cm ³
Reißfestigkeit/ Tear Strength DIN 53504	4 MPa
Reißdehnung/ Elongation At Break DIN 53504	400%
Druckverformungsrest / Compression Set ISO 815	70 h, 70°C = 36%
Weiterreißfestigkeit / Tear Resistance DIN 53515	25 N/mm
<u>Beständigkeit / Resistance</u>	
- Ozon / <i>Ozone</i>	gut / <i>good</i>
- Öl & Benzin / <i>Oil & Petrol</i>	nicht empfohlen / <i>not recommended</i>
- Säure / <i>Acid</i>	bedingt / <i>limited</i>
- Lauge / <i>Akaline</i>	bedingt / <i>limited</i>
Konformität / Conformity	UL94 V0 ab 3 mm, DIN 4102 B2

Jederzeitige Änderungen vorbehalten. Alle in diesem technischen Datenblatt enthaltenen Angaben stützen sich auf eine begrenzte Anzahl von Prüfungen an Normprüfkörpern aus Laborfertigung. Sie dienen nur als Anhaltspunkt und wurden vom Rohstofflieferant ohne Gewähr übernommen. Es obliegt dem Käufer, selbst zu prüfen, ob das Produkt für die vorgesehenen Anwendungen geeignet ist. / *Subject to change without prior notice. All information contained in this technical data sheet is based on a limited number of tests done on standard test specimens made by laboratory production. They are only intended as information and were extracted without guarantee from the raw material supplier. It is the buyer's obligation to check if the product is suitable for the intended application.*